

## Technical Information

**SURFYNOL® 465 Surfactant**

## Nonionic Dynamic Wetting Agent

**Description**

Surfynol® 465 surfactant can perform as a low-foaming dynamic wetting agent in a wide variety of applications including waterborne coatings, inks, adhesives, agricultural chemicals, and numerous industrial specialty applications. It is a 100% active, easy-to-handle liquid that contains no added alkylphenol ethoxylates (APEs) or hazardous air pollutants (HAPs). Surfynol®465 surfactant complies with several regulations needed for applications requiring food contact compliances in the US, Europe and Asia.

**Recommended Usage**

Between 0.1 and 2% of total formulation weight is recommended.

**Advantages**«Feature\_1»

- Low-foam dynamic surface tension reduction
- Enables wetting of low-energy and/or contaminated substrates
- Enhances rapid penetration of absorbent substrates
- Has several global food contact compliances
- Stable in most high electrolyte and brine systems
- Defoaming/de-airentrainment in concrete and oil field cements
- Wets and prevents smut formation in metalworking fluids

**Typical properties**

Appearance	Clear, yellow liquid
Density at 25 °C	1.04
Viscosity at 25°C	142 mPa.s
Flash Point	>110 °C
Pour Point	-6 °C
Activity	100 %

These are typical properties only and do not represent sales or manufacturing specifications.

**Applications**

- Waterborne industrial coatings
- Waterborne internal can coatings
- Printing inks
- Fountain solutions
- Adhesives
- Latex dipping
- Agricultural chemicals
- Metalworking lubricants
- Electroplating and acid pickling

**Storage and Handling**

Surfynol® 465 surfactant should be stored under dry and clean conditions between -10 °C and 50 °C.

Product is freeze-thaw stable; if it phase separates or freezes at colder temperatures, warm container to 40 °C and mix thoroughly before use. Please refer to Material Safety Data Sheet.

## Shelf-Life

60 months from the date of manufacture.

## Hazardous goods classification

Information concerning

- classification and labelling according to regulations for transport and for dangerous substances
- protective measures for storage and handling
- measures in case of accidents and fire
- toxicity and ecological effects

is given in our material safety data sheets.

06/2017

## For Technical Information, Support and Samples:

Americas: [prodinfo@evonik.com](mailto:prodinfo@evonik.com)

Asia: [picasia@evonik.com](mailto:picasia@evonik.com)

EMEA: [apcse@evonik.com](mailto:apcse@evonik.com)

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

**Evonik Nutrition & Care GmbH**  
Goldschmidtstraße 100  
45127 Essen, Germany  
Phone Europe +49 201 173 2665  
Phone Asia +86 21 61191 125  
Phone Americas +1 804 727 0700  
[interface-performance@evonik.com](mailto:interface-performance@evonik.com)  
[www.evonik.com/Interface-performance](http://www.evonik.com/Interface-performance)

